



(12) **EUROPEAN PATENT APPLICATION**
published in accordance with Art. 158(3) EPC

(43) Date of publication:
17.04.1996 Bulletin 1996/16

(21) Application number: 94919841.0

(22) Date of filing: 01.07.1994

(51) Int. Cl.⁶: **C08F 4/80**, C08F 12/08

(86) International application number: PCT/JP94/01078

(87) International publication number:
WO 95/01378 (12.01.1995 Gazette 1995/03)

(84) Designated Contracting States:
DE FR GB IT NL

(30) Priority: 02.07.1993 JP 164529/93

(71) Applicant: IDEMITSU KOSAN COMPANY LIMITED
Tokyo 100 (JP)

(72) Inventors:
• TAKEUCHI, Mizutomo
Ichihara-shi, Chiba-ken 299-01 (JP)

• SHOUZAKI, Hajime
Ichihara-shi, Chiba-ken 299-01 (JP)
• TOMOTSU, Norio
Ichihara-shi, Chiba-ken 299-01 (JP)


(74) Representative: Türk, Gille, Hrabal, Lelfert
Brucknerstrasse 20
D-40593 Düsseldorf (DE)

(54) **CATALYST FOR PRODUCING STYRENE POLYMER AND PROCESS FOR PRODUCING STYRENE POLYMER USING THE SAME**


(57) The present invention relates to a catalyst for producing a styrenic polymer which comprises a transition metal compound having a π -ligand, an indenyl group bearing at least one substituent group on the side of its five-membered ring; to a catalyst for producing a styrenic polymer which comprises (A) the above transition metal compound, (B) an aluminoxane and/or an ionic compound comprising a noncoordinate anion and a cation, and (C) a Lewis acid to be used as the case may be; and to a process for producing a styrenic polymer which comprises polymerizing a styrenic monomer or polymerizing a styrenic monomer along with an olefin or the like in the presence of the foregoing catalyst.

By the use of the highly active catalyst of the present invention, it is made possible to efficiently produce a styrenic polymer having a high degree of syndiotactic configuration.


more specifically, the compound represented by the general formula (I-b);



the compound represented by the general formula (II);



and the compound represented by the general formula (III), etc.



50 In the general formula (I-a), R stands for, as a π -ligand, an indenyl group bearing at least one substituent group on the side of its five-membered ring. In the general formula (I-a) and (I-b), M is a transition metal and exemplified by titanium, zirconium, hafnium, lanthanoids, niobium and tantalum, among which titanium is particularly preferable; X is a σ ligand and is exemplified by a hydrogen atom, a hydrocarbon group having 1 to 20 carbon atoms, an aromatic hydrocarbon group having 6 to 20 carbon atoms, an alkoxy group having 1 to 20 carbon atoms, an aryloxy group having 6 to 20 carbon atoms, a thioalkoxy group having 1 to 20 carbon atoms, a thioaryloxy group having 6 to 20 carbon atoms, an amino group, an amide group, a carboxyl group, an alkylsilyl group, and a halogen atom, and a plurality of X¹ may be the same or different and bonded to each other through an arbitrary group; L¹ is a Lewis base; (a+b+1) is the valency of M; and b is 0, 1, 2 or 3.

In the general formula (I-b), R¹ and R² are each a hydrogen atom, a hydrocarbon group having 1 to 20 carbon atoms, especially an alkyl group having 1 to 20 carbon atoms, an aromatic hydrocarbon group having 6 to 20 carbon atoms,

an alkoxy group having 1 to 20 carbon atoms, an aryloxy group having 6 to 20 carbon atoms, a thioalkoxy group having 1 to 20 carbon atoms, a thioaryloxy group having 6 to 20 carbon atoms, an amino group, an amide group, a carboxyl group, an alkylsilyl group, an indenyl group substituted with a halogen atom or the like with the proviso that at least one of R¹ is a group other than hydrogen atom; a plurality of R¹ may be the same or different; and a plurality of R² may be the same or different.

Specific examples of the R include 1-methylindenyl group; 2-methylindenyl group; 1-trimethylsilylindenyl group; 2-tert-butylindenyl group; 1,2-dimethylindenyl group; 1,3-dimethylindenyl group; 1,2,3-trimethylindenyl group; 1,2,3,4,7-pentamethylindenyl group; 1,4,5,6,7-pentamethylindenyl group; 1,3,4,5,6,7-hexamethylindenyl group; 1,3,4,5,6,7-hexamethylindenyl group; 1,2,3,4,5,6,7-heptamethylindenyl group; 1,2,3-trimethyl-4,7-dimethoxyindenyl group; and 1,2,3-trimethyl-4,7-difluoroindenyl group. Specific examples of X₁ include hydrogen atom, chlorine atom, bromine atom, iodine atom, methyl group, benzyl group, phenyl group, trimethylsilylmethyl group; methoxy group, ethoxy group, phenoxy group, thiomethoxy group, thiophenoxy group, dimethylamino group, and diisopropylamino group.

As the transition metal compound represented by the foregoing general formula (I-a) or (I-b), there are preferably usable the transition metal compounds containing R and X¹ optionally selected from among those as exemplified above.

In the general formula (II), R³ is the same as R¹ as defined above with the proviso that at least one of R³ is a group other than hydrogen atom, and a plurality of R³ may be the same or different; R⁴ is the same as R² as defined above, and a plurality of R⁴ may be the same or different; M², X², L², c and b are each the same as M¹, X¹, L¹, a and b, respectively; a plurality of X² may be the same or different and bonded to each other through an arbitrary group; Q¹ is a hydrocarbon group having 1 to 6 carbon atoms, an aromatic hydrocarbon group having 6 to 20 carbon group, a silylene group having 1 to 5 silicon atoms, a germylene group having 1 to 5 germanium group; and J¹ is an amide group, a phosphide group, oxygen atom, sulfur atom, an alkylidene group, or the like.


Further in the general formula (III), R⁵ is the same as R¹ as defined above with the proviso that at least one of R⁵ is a group other than hydrogen atom, and a plurality of R⁵ may be the same or different; R⁶ is the same as R² and a plurality of R⁶ may be the same or different; M³, X³, L³, e, f, Q² and J² are each the same as M¹, X¹, L¹, a, b, Q¹ and J¹, respectively; and a plurality of X³ may be the same or different and bonded to each other through an arbitrary group.

As the transition metal compound represented by the above-mentioned general formula (II) or (III), mention is made of, for example, (tert-butylamide)(2,3-dimethylindenyl)-1,2-ethanediyttitanium dichloride; (tert-butylamide)(2,3-dimethylindenyl)-1,2-ethanediyldimethyltitanium; (tert-butylamide)(2,3-dimethylindenyl)-dimethylsilyltitanium dichloride; (tert-butylamide)(2,3-dimethylindenyl)-dimethylsilyldimethyltitanium; (tert-butylamide)(1,3-dimethylindenyl)-dimethylsilyltitanium dichloride; (tert-butylamide)(1,3-dimethylindenyl)-dimethylsilyldimethyltitanium; (tert-butylamide)(2,3,4,5,6,7-hexamethylindenyl)-dimethylsilyltitanium dichloride; (tert-butylamide)(2,3,4,5,6,7-hexamethylindenyl)-dimethylsilyldimethyltitanium; (tert-butylamide)(1,3,4,5,6,7-hexamethylindenyl)-dimethylsilyltitanium dichloride; (tert-butylamide)(1,3,4,5,6,7-hexamethylindenyl)-dimethylsilyldimethyltitanium; (2,3-dimethylindenyl)-1-ethane-2-oxatitanium dichloride; (2,3-dimethylindenyl)-1-ethane-2-oxadimethyltitanium; (phenylamide)(2,3-dimethylindenyl)-1,2-ethanediytzirconium dichloride; (tert-butylamide)(2,3-dimethylindenyl)-1,2-ethanediyldimethylzirconium; (tert-butylamide)(2,3-dimethylindenyl)-dimethylsilyldimethylzirconium; (tert-butylamide)(1,3-dimethylindenyl)-dimethylsilyltitanium dichloride; (tert-butylamide)(1,3-dimethylindenyl)-dimethylsilyldimethylzirconium; (tert-butylamide)(2,3,4,5,6,7-hexamethylindenyl)-dimethylsilyltitanium dichloride; (tert-butylamide)(2,3,4,5,6,7-hexamethylindenyl)-dimethylsilyldimethylzirconium; (tert-butylamide)(1,3,4,5,6,7-hexamethylindenyl)-dimethylsilyltitanium dichloride; (tert-butylamide)(1,3,4,5,6,7-hexamethylindenyl)-dimethylsilyldimethylzirconium; (2,3-dimethylindenyl)-1-ethane-2-oxazirconium dichloride; (2,3-dimethylindenyl)-1-ethane-2-oxadimethyl-zirconium and the like.


The catalyst according to the present invention may contain one or not less than two kinds of the above-mentioned transition metal compounds.

The catalyst according to the present invention comprises a transition metal compound having as a π -ligand, an indenyl group bearing at least one substituent group on the side of its five-membered ring, and it is particularly preferable that the catalyst comprises (A) the above-mentioned transition metal compound and (B) an aluminoxane and/or an ionic compound comprising a noncoordinate anion and a cation, or that the catalyst comprises (A) the above-mentioned transition metal compound, (B) an aluminoxane and/or an ionic compound comprising a noncoordinate anion and a cation and (C) a Lewis acid.

The aluminoxane as the aforesaid component (B) is obtained by bringing an organoaluminum compound into contact with a condensation agent and is exemplified by chain aluminoxane represented by the general formula (IV)



wherein R⁷ is an alkyl group having 1 to 20 carbon atoms and p is a number of 0 to 50, preferably 5 to 30; and cyclic aluminoxane represented by the general formula (V)



Wherein R⁷ is as previously defined; and q is a number of 2 to 50, preferably 5 to 30.

Examples of the organoaluminum compound to be used as a starting material for the aluminoxane include a trialkylaluminum such as trimethylaluminum, triethylaluminum, triisobutylaluminum and a mixture thereof. Examples of the condensation agent is water as a typical one and optionally a material capable of undergoing a condensation reaction with the trialkylaluminum which material is exemplified by water adsorbed in an inorganic matter and diol.

Examples of the ionic compound comprising a noncoordinate anion and a cation as the component (B) include a compound represented by the general formula (VII) or (VIII)



wherein L⁵ is M⁶, R⁸R⁹M⁷ or R¹⁰C as hereinafter described; L⁴ is a Lewis base; M⁴ and M⁵ are each an element selected from Groups 5 to 15 of the Periodic Table and exemplified by B, Al, P, As and Sb; M⁶ is an element selected from Groups 8 to 12 of the Periodic Table and exemplified by Ag and Cu; M⁷ is an element selected from Groups 8 to 10 of the Periodic Table and exemplified by Fe, Co and Ni; Y¹ to Yⁿ are each a hydrogen atom, dialkylamino group, alkoxy group, aryloxy group, alkyl group having 1 to 20 carbon atoms, aryl group having 6 to 20 carbon atoms, arylalkyl group, alkylaryl group, substituted alkyl group, organometalloid group or halogen atom and exemplified by dimethylamino group, diethylamino group, methoxy group, ethoxy group, butoxy group, phenoxy group, 2,6-dimethylphenoxy group, methyl group, ethyl group, propyl group, butyl group, octyl group, phenyl group, tolyl group, xylyl group, mesityl group, benzyl group, pentafluorophenyl group, 3,5-di(trifluoromethylphenyl) group, 4-tert-butylphenyl group, F, Cl, Br, I, pentamethylantimony group, trimethylsilyl group, trimethylgermyl group and diphenylboron group; R⁸ and R⁹ are each a cyclopentadienyl group, substituted cyclopentadienyl group, indenyl group, substituted indenyl group or fluorenyl group and exemplified by methylcyclopentadienyl group and pentamethylcyclopentadienyl group; R¹⁰ is an alkyl group, aryl group or a substituted aryl group, may be the same or different and exemplified by a phenyl group, 4-methoxyphenyl group and 4-methylphenyl group; m is the valency of each of M⁴ and M⁵, indicating an integer from 1 to 7; n is an integer from 2 to 8; g is the ion valency of each of [L⁴-H] and [L⁵], indicating an integer from 1 to 7; h is an integer of 1 or greater and i=(h x g)/(n-m).

Examples of the noncoordinate anion in the aforesaid ionic compound include (tetraphenyl)borate; tetra(fluorophenyl)borate; tetrakis(difluorophenyl)borate; tetrakis(trifluorophenyl)borate; tetrakis(tetrafluorophenyl)borate; tetrakis(pentafluorophenyl)borate; tetrakis(trifluoromethylphenyl)borate; tetra(tolyl)borate; tetra(xylyl)borate; (triphenylpentafluorophenyl)borate; [tris(pentafluorophenyl)phenyl]borate and tridecahydride-7,8-dicarbaundecaborate. Examples of the cation in the above-mentioned ionic compound include triethyl ammonium; tributyl ammonium; N,N'-dimethylanilinium; N,N'-diethylanilinium; triphenylphosphonium; dimethylphenylphosphonium; 1,1'-dimethylferrocene;

decamethylferrocene; silver (I); triphenyl carbenium; tritolylcarbenium; trimethoxyphenylcarbenium; [di(tolyl)phenyl]carbenium; [di(methoxyphenyl)phenyl]carbenium and [methoxyphenyl-di(phenyl)]carbenium.

The above-mentioned ionic compound can preferably be used by optionally selecting the noncoordinate anion and cation from among the above-exemplified examples and combining the selected ones.

5 In the catalyst of the present invention, the aluminosilane as the component (B) may be used alone or in combination with at least one other, the ionic compound also as the component (B) may be used alone or in combination with at least one other, and further at least one such aluminosilane may be used in combination with at least one such ionic compound.

Examples of the Lewis acid as the component (C) to be used when desired in the catalyst of the present invention include an organoaluminum compound, an organoboron compound, a magnesium compound, a zinc compound and a
10 lithium compound. Examples of the usable organoaluminum compound include the compound represented by the general formula (VIII)



15 wherein R^{11} and R^{12} are each an alkyl group having 1 to 8 carbon atoms and may be the same or different; Z^1 is a halogen atom; and r , s , t and u are numbers each satisfying the relations $0 < r \leq 3$, $0 < s \leq 3$, $0 \leq t < 3$, $0 \leq u < 3$ and $r+s+t+u=3$.

In the organoaluminum compound represented by the general formula (VIII), the compound wherein $t=u=0$ and $r=3$ is exemplified by trimethylaluminum, triethylaluminum, triisopropylaluminum, triisobutylaluminum and trioctylaluminum. Example of the compound corresponding to the case where $t=u=0$ and $1.5 \leq r < 3$, include diethylaluminum ethoxide, 20 dibutylaluminum butoxide, diethylaluminum sesquithoxide and dibutylaluminum sesquibutoxide; as well as partially alkoxyated alkylaluminum. Examples of the compound corresponding to the case where $s=t=0$ include diethylaluminum dichloride and dibutylaluminum dichloride ($r=2$); ethylaluminum sesquichloride and butylaluminum sesquichloride ($r=1.5$); and ethylaluminum dichloride and butylaluminum dichloride ($r=1$). Examples of the compound corresponding to the case where $s=u=0$ include diethylaluminum hydride and diisobutylaluminum hydride ($r=2$); and ethylaluminum dihy-
25 dride and butylaluminum dihydride ($r=1$).

Examples of the organoboron compounds usable as the component (C) include the compound represented by the general formula (IX)



30 wherein R^{13} is a hydrocarbon group having 1 to 20 carbon atoms, an aromatic hydrocarbon group having 6 to 20 carbon atoms, a substituted aromatic hydrocarbon group, hydrogen atom or a halogen atom, may be the same or different and specifically exemplified by a phenyl group, tolyl group, fluorophenyl group, trifluoromethylphenyl group, pentafluorophenyl group, fluorine atom, chlorine atom, bromine atom and iodine atom; L^6 is a Lewis base and exemplified by an ether compound such as diethyl ether and tetrahydrofuran and an amine compound such as pyridine; and v is an integer from zero (0) to 3.

Examples of the above-mentioned magnesium compound include a Grignard compound such as methylmagnesium bromide, ethylmagnesium bromide, phenylmagnesium bromide and benzylmagnesium bromide, an organomagnesium compound such as diethoxymagnesium and ethylbutylmagnesium and an inorganic magnesium compound such as magnesium chloride. In addition, mention may be made of a zinc compound exemplified by an organozinc compound such as diethylzinc and of a lithium compound exemplified by an organolithium compound such as methyllithium.

In the catalyst according to the present invention, the aforestated Lewis acid as the component (C) may be used alone or in combination with at least one other.

The catalyst according to the present invention, which comprises the components (A) and (B) or the components (A), (B) and (C), may be incorporated further with an other catalyst component. The blending ratio of each of the components varies depending upon various conditions and thus can not be determined unequivocally, but the molar ratio of the component (A) to the component (B) is usually selected in the range of preferably 1 : 1 to 1 : 10000, more preferably 1 : 1 to 1 : 1000 in the case of the component (B) being an aluminosilane, and it is usually selected in the range of preferably 0.1 : 1 to 1 : 0.1 in the case of the component (B) being an ionic compound. The molar ratio of the component (A) to the
50 component (C) when used, is selected in the range of preferably 1 : 0.1 to 1 : 1000.

As a method for contact-mixing the components (A) and (B) and the component (C) to be used when desired, mention may be made of ① a method in which the component (C) is added to the contact mixture between the components (A) and (B) to form a catalyst, which is brought into contact with a monomer component to be polymerized; ② a method in which the component (A) is added to the contact mixture between the components (B) and (C) to form a catalyst, which is brought into contact with a monomer component to be polymerized; ③ a method in which the component (B) is added to the contact mixture between the components (A) and (C) to form a catalyst, which is brought into contact with a monomer component to be polymerized; ④ a method in which the components (A), (B) and (C) are each separately brought into contact with a monomer component to be polymerized; and ⑤ a method in which the catalyst
55

prepared in the above-mentioned ①, ② or ③ is brought into contact with the contact mixture between the monomer component to be polymerized and the component (C).

The contact mixing among the components (A) and (B) and the component (C) to be used as desired can be carried out at a temperature in the range of -20 to 200°C, needless to say, at a polymerization temperature.

5 In the process according to the present invention, a styrenic polymer is produced by polymerizing, in the presence of the above-described catalyst, an (a) styrenic monomer alone or an (a) styrenic monomer along with (b) at least one compound selected from olefins, diolefins and alkynes.

Examples of the styrenic monomer as the aforesaid monomer component (a) include styrene, alkylstyrenes such as p-methylstyrene; m-methylstyrene; o-methylstyrene; 2,4-dimethylstyrene; 2,5-dimethylstyrene; 3,4-dimethylstyrene; 10 3,5-dimethylstyrene; and p-tertiary-butylstyrene; halogenated styrenes such as p-chlorostyrene; m-chlorostyrene; o-chlorostyrene; p-bromostyrene; m-bromostyrene; o-bromostyrene; p-fluorostyrene; m-fluorostyrene; o-fluorostyrene and o-methyl-p-fluorostyrene; organosiliconated styrenes, vinylbenzoic acid esters and divinylbenzene. Any of the above-mentioned styrenic monomer may be used alone or in combination with at least one other.

On the other hand, examples of the olefins as the aforesaid monomer component (b) include α -olefins such as 15 ethylene; propylene; butene-1; pentene-1; hexene-1; heptene-1; octene-1; nonene-1; decene-1; 4-phenylbutene-1; 6-phenylhexene-1; 3-methylbutene-1; 4-methylpentene-1; 3-methylpentene-1; 3-methylhexene-1; 4-methylhexene-1; 5-methylhexene-1; 3,3-dimethylpentene-1; 3,4-dimethylpentene-1; 4,4-dimethylpentene-1; vinylcyclohexane; and vinylcyclohexene, halogen-substituted α -olefins such as hexafluoropropene; tetrafluoroethylene; 2-fluoropropene; fluoroethylene; 1,1-difluoroethylene; 3-fluoropropene; trifluoroethylene; and 3,4-dichlorobutene-1, cyclic olefins such as 20 cyclopentene; cyclohexene; norbornene; 5-methylnorbornene; 5-ethylnorbornene; 5-propylnorbornene; 5,6-dimethylnorbornene; 1-methylnorbornene; 7-methylnorbornene; 5,5,6-trimethylnorbornene; 5-phenylnorbornene; 5-benzylnorbornene; and 5-vinylnorbornene. Examples of the diolefins include straight chain diolefins such as butadiene; isoprene; and 1,6-hexadiene, and cyclic diolefins such as norbornadiene; 5-ethylidenenorbornene; and dicyclopentadiene. Example of the alkynes include acetylene, methylacetylene, phenylacetylene and trimethylsilylacetylene. The above-mentioned monomer may be polymerized alone or in combination with at least one other monomer.

The polymerization method may be bulk polymerization method without specific limitation. The polymerization may be carried out in an aliphatic hydrocarbon solvent such as pentane, hexane and heptane, an alicyclic hydrocarbon solvent such as cyclohexane or an aromatic hydrocarbon solvent such as benzene, toluene, xylene and ethylbenzene. The polymerization temperature is not specifically limited but is usually 0 to 200°C, preferably 20 to 100°C. In the case where 30 a gaseous monomer is employed, the partial pressure of the gaseous monomer is usually 300 kg/cm² or lower, preferably 30 kg/cm² or lower.

The styrenic polymer obtained in such a way has a high degree of syndiotactic configuration in its aromatic vinyl chain when it is contained in the polymer. In this case, a high degree of syndiotactic configuration in the aromatic vinyl chain of the styrenic polymer or styrenic copolymer signifies that its stereochemical structure is of high degree of syndiotactic configuration, i.e., the stereostructure in which phenyl groups or substituted phenyl groups as side chains 35 are located alternately at opposite directions relative to the main chain consisting of carbon-carbon bonds. Tacticity is quantitatively determined by the nuclear magnetic resonance method (¹³C-NMR method) using carbon isotope. The tacticity as determined by the ¹³C-NMR method can be indicated in terms of proportions of structural units continuously connected to each other, i.e., a diad in which two structural units are connected to each other, a triad in which three structural units are connected to each other and a pentad in which five structural units are connected to each other. "The styrenic polymers having such a high degree of syndiotactic configuration" as mentioned in the present invention usually means polystyrene, poly(substituted styrene), poly(vinyl benzoate), the mixture thereof, and copolymers containing the above polymers as main components, having such a syndiotacticity that the proportion of racemic diad is at least 75%, preferably at least 85%, or the proportion of racemic pentad is at least 30%, preferably at least 50%. Examples 45 of the poly(substituted styrene) include poly(hydrocarbon group-substituted styrene) such as poly(methylstyrene), poly(ethylstyrene), poly(isopropylstyrene), poly(phenylstyrene) and poly(vinylstyrene); poly(halogenated styrene) such as poly(chlorostyrene), poly(bromostyrene), and poly(fluorostyrene); and poly(alkoxystyrene) such as poly(methoxystyrene) and poly(ethoxystyrene).

In the following, the present invention will be described in more detail with reference to examples, which however 50 shall not be construed to limit the invention thereto.

The reaction in each of the synthesis examples was carried out in an atmosphere of dry nitrogen or in a stream of nitrogen unless otherwise noted.

Synthesis Example 1

Synthesis of 1,2,3,4,5,6,7-heptamethylindenyltitanium trichloride (Compound A) ---

5 (1) Synthesis of 2,3,4,5,6,7-hexamethylindane-1-one ---

Aluminum trichloride in an amount of 58.7g (440 mmol) was suspended in 300 mL (milliliter) of dried carbon disulfide (dried and distilled on calcium hydride) and was brought to an ice-cooling temperature. Then, 47.4g (400 mmol) of tigloyl chloride was mixed with 53.7g (400 mmol) of tetramethylbenzene, and the resultant mixture was added dropwise to the
 10 above-produced carbon disulfide solution, followed by continuous stirring at room temperature. As the result, a brown to reddish brown solution was produced. After 2 hours of stirring, the solution was allowed to react for another 2 hours under refluxing with the result that the solution turned orange in color.

The resultant reaction mixture was brought back to room temperature and thereafter, was poured onto the mixture of 500g of water and 500 mL of concentrated hydrochloric acid, followed by stirring for about one hour. Then, the resultant
 15 product was subjected to extraction and separation twice with 400 mL each of ether, further with 200 mL each of ether twice. The ether phases thus produced were combined together, and dried with calcium chloride anhydride as the drying agent. After filtering away the used drying agent, the ether was distilled away and the brown viscous solid thus obtained was dissolved in hexane to recrystallize the solid therefrom. The procedure of allowing the solution saturated at room temperature to stand at -20°C and collecting the precipitate by means of filtration was repeated to afford 75.9g of
 20 2,3,4,5,6,7-hexamethylindane-1-one as a reddish yellow solid.

(2) Synthesis of 1,2,3,4,5,6,7-heptamethylindene ---

2,3,4,5,6,7-Hexamethylindane-1-one in an amount of 37.3g (172 mmol) was dissolved in 200 mL of dehydrated
 25 ether (distilled on metallic sodium), and to the resultant solution was added dropwise 120 mL of a 1.4 M solution of methylolithium in ether under ice-cooling. After one hour from the addition, the solution turned from reddish brown to reddish yellow and further to clear yellow, was brought back to room temperature and was allowed to react for one hour and for additional 2 hours, under heating refluxing to complete the reaction. The reaction product was quenched under ice-cooling with 20 mL of water and then with 150 mL of 1 N aqueous solution of ammonium chloride to separate the
 30 organic phase. The separated organic phase was subjected to extraction and separation twice repeatedly with 100 mL each of ether, and the organic phases thus produced were combined together, washed with saturated aqueous solution of sodium chloride and was dried with magnesium sulfate anhydride as the drying agent. After the used drying agent was filtered away, the ether solution was subjected to dehydration reaction by incorporating with small pieces of iodine in an atmosphere of nitrogen for replacing, allowed to stand overnight in an atmosphere of nitrogen, and was subjected
 35 to heating refluxing for 3 hours to complete the reaction. The reaction product thus obtained was washed twice with 150 mL each of 0.2 N aqueous solution of sodium hydrosulfite and twice with 150 mL each of saturated aqueous solution of sodium chloride, and dried with magnesium sulfate anhydride as the drying agent.

Subsequently, by filtering away the used drying agent and distilling away the ether, there was produced brown crude 1,2,3,4,5,6,7-heptamethylindene, which was dissolved again in 300 mL of hexane and dried with magnesium sulfate
 40 anhydride as the drying agent to afford a yellow solution. Then, by filtering away the used drying agent and distilling away the hexane, there was produced an orange-colored oil, which was adsorbed onto 100g of silica-gel column and eluted with hexane to afford 24.3g (113 mmol) of objective 1,2,3,4,5,6,7-heptamethylindene in the form of yellow solid in a yield rate of 65.7%.

45 (3) Synthesis of 1,2,3,4,5,6,7-heptamethylindenyltrimethylsilane ---

1,2,3,4,5,6,7-Heptamethylindene in an amount of 24.3g (113 mmol) was dissolved in 150 mL of dried hexane, to the resultant solution was added 1 mL of hexamethyl phosphoamide (HMPA), and to the mixture thus formed was added dropwise, under ice-cooling, 80 mL of a 1.7 M solution of tert-butyllithium in pentane. After 2 hours from the addition,
 50 1,2,3,4,5,6,7-heptamethylindenyltitanium thus produced was settled, subjected to decantation for separating the solution and washed three times with 100 mL each of hexane to afford yellowish white solid. The solid thus obtained was dissolved in 150 mL of dehydrated tetrahydrofuran (THF) to form a red solution, which was incorporated under ice-cooling with 13.0g (120 mmol, 15.2 mL) of trimethylchlorosilane (TMSCl) that had been subjected to simple distillation, was brought back to room temperature and was allowed to stand overnight.

The yellow solution thus obtained was incorporated with 20 mL of water for quenching and THF was removed under reduced pressure. Then, the solution was extracted and separated with 500 mL of hexane, the organic phase thus
 55 obtained was dried with magnesium sulfate anhydride as the drying agent, the used drying agent was filtered away, and the volatile components were distilled away under reduced pressure. As the result, there was produced 1,2,3,4,5,6,7-

EP 0 707 013 A1

heptamethylindenyltrimethylsilane in the form of yellowish white solid in a yield of 19.5g (62.2 mmol) and in a yield rate of 55%.

The product was analyzed by $^1\text{H-NMR}$ by the use of trimethylsilane as the standard and heavy chloroform (CDCl_3) as the solvent with the results as follows:

$^1\text{H-NMR}$: 2.60ppm (3H, s), 2.40ppm (3H, s), 2.33ppm (3H, s), 2.31ppm (3H, s), 2.28ppm (3H, s), 1.99ppm (3H, s), 1.64ppm (3H, s), -0.09ppm (9H, s)

(4) Synthesis of 1,2,3,4,5,6,7-heptamethylindenyltitanium trichloride ---


Titanium tetrachloride in an amount of 15.2g (80 mmol, 8.8 mL) was dissolved in 100 mL of dehydrated toluene, and to the resultant solution was added dropwise, at room temperature, a solution of 19.52g of 1,2,3,4,5,6,7-heptamethylindenyltrimethylsilane in 150 mL of toluene over a period of 3 hours. After one hour of heating refluxing of the mixed solution thus obtained, there was produced a toluene-soluble portion at 80°C, which then was extracted twice with 100 mL each of toluene. By filtering off the toluene-insoluble portion, there was obtained a green toluene solution, and the volatile components of which were distilled away at 40°C under reduced pressure to afford dark green solid. Thereafter, the solid was incorporated with 20 mL of toluene and then with 200 mL of hexane, and the insoluble portion was collected by filtration as the objective product in a yield of 9.43g (26 mmol) and in a yield rate of 39%. The product was slightly soluble in boiling hexane, readily soluble in toluene, and was analyzed by NMR with the results as follows:

$^1\text{H-NMR}$ (tetramethylsilane as the standard and heavy chloroform (CDCl_3) as the solvent);

2.90ppm (6H, s), 2.68ppm (6H, s), 2.46ppm (3H, s), 2.38ppm (6H, s), $^{49}\text{Ti-NMR}$ (titanium tetrachloride as the standard and CDCl_3 as the solvent); 19.55ppm.

EP 0 707 013 A1

The schematic synthesis process for compound A is illustrated as follows:



Synthesis Example 2

Synthesis of 1,2,3,4,5,6,7-heptamethylindenylmethyltitanium trimethoxide (compound B) ---

45 1.48g (4 mmol) of 1,2,3,4,5,6,7-heptamethylindenyltitanium trichloride which had been synthesized in Synthesis Example 1 was dissolved in 20 mL of dehydrated toluene in an atmosphere of nitrogen, and to the resultant solution were added, under ice-cooling, 0.64g (20 mmol, 0.8 mL) of dehydrated methanol and then 2.03g (20 mmol, 2.8 mL) of dehydrated triethylamine. After 30 minutes from the addition, the mixture was brought back to room temperature and stirred overnight. Subsequently, the volatile components in the mixture were distilled away at room temperature under

50 reduced pressure, the nonvolatile portion was extracted by adding thereto 80 mL of dried hexane, and the hexane-insoluble portion was removed with a glass filter. By distilling away the remaining hexane from the resultant yellow filtrate under reduced pressure, there was obtained the title compound in the form of red solid in a yield of 1.30g (4 mmol) and in a yield rate of 100%.

55 The product was analyzed by ¹H-NMR by the use of tetramethylsilane as the standard and CDCl₃ as the solvent with the results as follows: ¹H-NMR; 2.45ppm (6H, s), 2.46ppm (6H, s), 2.20ppm (6H, s), 2.04ppm (3H, s), 0.614ppm (6H, s).

Synthesis Example 3

Synthesis of 1,2,4,5,6,7-hexamethylindenyltitanium trichloride (Compound C) ---

5 (1) Synthesis of 1,2,4,5,6,7-Hexamethylindene

Lithium aluminum hydride (LAH) in an amount of 3.09g (81 mmol) was suspended in dried ether (distilled on metallic sodium). 38.7g (180 mmol) of 2,3,4,5,6,7-hexamethylindane-1-one which had been synthesized in Synthesis Example 1 was dissolved in 200 mL of dried ether, and the resultant ether solution was added dropwise to the above-prepared
 10 suspension of LAH at a rate causing mild reflux. The dropwise addition was completed over a period of 1.5 hour, and thereafter stirring was continued for 2.5 hours under heating refluxing. The reaction product was quenched under ice-cooling with 20 mL of water and then with 200 mL of 1 N aqueous solution of ammonium chloride to separate the organic phase. The separated organic phase was subjected to extraction and separation twice repeatedly with 100 mL each of ether, and the organic phases thus produced were combined together, washed with saturated aqueous solution of sodium
 15 chloride and was dried with magnesium sulfate anhydride as the drying agent. After the used drying agent was filtered away, the ether solution was subjected to dehydration reaction by incorporating with small pieces of iodine in an atmosphere of nitrogen for replacing, allowed to stand overnight in an atmosphere of nitrogen, and was subjected to heating refluxing for 3 hours to complete the reaction. The reaction product thus obtained was washed twice with 150 mL each of 0.2 N aqueous solution of sodium hydrosulfite and twice with 150 mL each of saturated aqueous solution of sodium
 20 chloride, and dried with magnesium sulfate anhydride as the drying agent.

Subsequently, by filtering away the used drying agent and distilling away the ether, there was produced yellow crude 1,2,4,5,6,7-hexamethylindene, which was dissolved again in 300 mL of hexane and dried with magnesium sulfate anhydride as the drying agent to afford a yellow solution. Then, by filtering away the used drying agent and distilling away the hexane, there was produced a yellow solid, the solution of which in hexane, was adsorbed onto 20g of silica-gel.
 25 The resultant slurry in hexane was developed in 80g of silica-gel column and eluted with hexane to afford 28.8g (144 mmol) of objective 1,2,4,5,6,7-hexamethylindene in the form of yellowish white solid in a yield rate of 80.4%.

(2) Synthesis of 1,2,4,5,6,7-hexamethylindenyltrimethylsilane ---

1,2,4,5,6,7-Hexamethylindene in an amount of 14.4g (72 mmol) was dissolved in 150 mL of dried hexane, to the resultant solution was added 0.5 mL of hexamethyl phosphoamide (HMPA), and to the mixture thus formed was added dropwise 47 mL of a 1.7 M solution of tert-butyllithium in pentane. After 2 hours from the addition, 1,2,4,5,6,7-hexamethylindenyl lithium thus produced was settled, subjected to decantation for separating the solution and washed three
 35 times with 100 mL each of hexane to afford yellowish white solid. The solid thus obtained was dissolved in 100 mL of dehydrated tetrahydrofuran (THF) to form a red solution, which was incorporated under ice-cooling with 8.7g (80 mmol, 10.2 mL) of trimethylchlorosilane (TMSCl) that had been subjected to simple distillation, was brought back to room temperature and was allowed to stand overnight.

The yellow solution thus obtained was incorporated with 20 mL of water for quenching and THF was removed under reduced pressure. Then the solution was extracted and separated with 500 mL of hexane, the organic phase thus
 40 obtained was dried with magnesium sulfate as the drying agent, the used drying agent was filtered away, and the volatile components were distilled away under reduced pressure. As the result, there was produced 1,2,4,5,6,7-hexamethylindenyltrimethylsilane in the form of yellow solid in a yield of 18.0g (60.4 mmol) and in a yield rate of 84%.


(3) Synthesis of 1,2,4,5,6,7-hexamethylindenyltitanium trichloride ---

45 Titanium tetrachloride in an amount of 15.2g (80 mmol, 8.8 mL) was dissolved in 100 mL of dehydrated toluene, and to the resultant solution was added dropwise, at room temperature, a solution of 18.02g of 1,2,4,5,6,7-hexamethylindenyltrimethylsilane in 150 mL of toluene over a period of 3 hours. After one hour of heating refluxing of the mixed solution thus obtained, there was produced a toluene-soluble portion at 80°C, which then was extracted twice with 100 mL each
 50 of toluene. By filtering off the toluene-insoluble portion, there was obtained a green toluene solution, and the volatile components of which were distilled away at 40°C under reduced pressure to afford dark green solid. Thereafter, the solid was incorporated with 20 mL of toluene and then with 200 mL of hexane, and the insoluble portion was collected by filtration. The insoluble portion was subjected to Soxhlet extraction by using boiling hexane to recover the title complex at 88% recovery rate from the extract solution in a yield of 21.07g (60 mmol) and in a yield rate of 75%. The product
 55 was readily soluble in toluene, and was analyzed by NMR with the results as follows:

¹H-NMR(tetramethylsilane as the standard and heavy chloroform (CDCl₃) as the solvent); 6.89ppm (3H, s), 2.86ppm (3H, s), 2.68ppm (3H, s), 2.53ppm (3H, s), 2.47ppm (3H, s), 2.37ppm (3H, s), 2.35ppm (3H, s), ⁴⁹Ti-NMR(titanium tetrachloride as the standard and CDCl₃ as the solvent); -75.54ppm.

EP 0 707 013 A1

The schematic synthesis process for compound C is illustrated as follows;



Synthesis Example 4

Synthesis of 1,2,4,5,6,7-hexamethylindenyltrimethyltitanium (Compound D) ---

1,2,4,5,6,7-Hexamethylindenyltitanium trichloride in an amount of 0.88g (2.5 mmol) which had been synthesized in Synthesis Example 3 was dissolved in 50 mL of dehydrated THF in an atmosphere of nitrogen. The resultant solution was incorporated at -78°C with 9.0 mL of 1.0 M solution of methylmagnesium bromide in THF, and after the elapse of 15 minutes was gradually brought back to room temperature, with the result that the solution turned to yellowish brown gradually. After the elapse of 15 minutes, the volatile components in the solution were distilled away under reduced pressure to leave only the bone-dried matter, which was extracted with a total quantity of 250 mL of dried hexane. The hexane-insoluble portion was filtered off, and the volatile components in the filtrate solution were distilled away to afford a brown oil in a yield of 0.62g (2.1 mmol) and in a yield rate of 85%. The oil was allowed to stand overnight in a refrigerator with the result that the oil turned to a brown solid.

The resultant solid was analyzed by ¹H-NMR by the use of tetramethylsilane as the standard and CDCl₃ as the solvent with the results as follows:

¹H-NMR; 6.23ppm (1H, s), 2.52ppm (3H, s), 2.47ppm (3H, s), 2.26ppm (3H, s), 2.21ppm (3H, s), 2.20ppm (3H, s), 2.14ppm (3H, s), 0.65ppm (9H, s).

Synthesis Example 5

Synthesis of 1,2,3-trimethylindenyltitanium trichloride (Compound E) ---

5 (1) Synthesis of 2,3-dimethylindane-1-one ---

Aluminum trichloride in an amount of 30.7g (250 mmol) was suspended in 150 mL of dried carbon disulfide (dried and distilled on calcium hydride) and was brought to an ice-cooling temperature. Then, 25.1g (212 mmol) of tigloyl chloride was mixed with 16.6g (212 mmol) of benzene, and to the resultant mixture was added dropwise the above-
 10 produced carbon disulfide solution, followed by continuous stirring at room temperature. As the result, a yellow solution was gradually produced. The solution was allowed to stand overnight, with the result that the solution was separated into two phases including a brown phase and a colorless phase. The solution was allowed to react for another 5 hours under refluxing. The resultant reaction mixture was brought back to room temperature and thereafter, was poured onto the mixture of 250g of water and 250 mL of concentrated hydrochloric acid, followed by stirring for about one hour. Then,
 15 the resultant product was subjected to extraction and separation four times repeatedly with 200 mL each of ether. The ether phases thus produced were combined together, and dried with calcium chloride anhydride as the drying agent. After filtering away the used drying agent, the ether was distilled away and the brown viscous oil was obtained. Because of its being readily soluble in hexane, the oil was again dissolved in hexane, and the resultant solution was washed twice with 150 mL each of saturated aqueous solution of sodium carbonate and twice with 150 mL each of saturated aqueous
 20 solution of sodium chloride, and dried with magnesium sulfate anhydride. By distilling away the hexane, there was obtained 19.9g of 2,3-dimethylindane-1-one.

(2) Synthesis of 1,2,3-trimethylindene ---

2,3-dimethylindane-1-one in an amount of 19.2g (124 mmol) was dissolved in 100 mL of dehydrated ether (distilled on metallic sodium) and to the resultant solution was added dropwise 100 mL of a 1.4M solution of methylolithium in ether under ice-cooling. After one hour from the addition, the solution turned to violet color, was brought back to room temperature and was allowed to react for 2 hours under heating refluxing to complete the reaction. The reaction product was quenched under ice-cooling with 20 mL of water and then with 100 mL of 1 N aqueous solution of ammonium chloride
 30 to separate the organic phase. The separated organic phase was subjected to extraction and separation twice repeatedly with 100 mL each of ether and the organic phases thus produced were combined together, washed with saturated aqueous solution of sodium chloride and was dried with magnesium sulfate anhydride as the drying agent. After the used drying agent was filtered away, the ether solution was subjected to dehydration reaction by incorporating with small pieces of iodine in an atmosphere of nitrogen for replacing, allowed to stand overnight in an atmosphere of nitrogen,
 35 and was subjected to heating refluxing for 3 hours to complete the reaction. The reaction product thus obtained was washed twice with 150 mL each of 0.2 N aqueous solution of sodium hydrosulfite and twice with 150 mL each of saturated aqueous solution of sodium chloride, and dried with magnesium sulfate anhydride as the drying agent.

Subsequently, by filtering away the used drying agent and distilling away the ether, there was produced brown crude 1,2,3-trimethylindene, which was dissolved again in 200 mL of hexane and dried with magnesium sulfate anhydride as
 40 the drying agent to afford a brown solution. Then, by filtering away the used drying agent and distilling away the hexane, there was produced an brown-colored oil, the solution of which in hexane was adsorbed onto 20g of silica-gel column. The adsorbed oil in 80g of silica-gel was eluted with hexane to afford the objective 1,2,3-trimethylindene in the form of orange-colored oil in a yield of 4.09g and in a yield rate of 20.8%.

45 (3) Synthesis of 1,2,3-trimethylindenyltrimethylsilane


1,2,3-Trimethylindene in an amount of 4.09g (26 mmol) was dissolved in 100 mL of dried THF, and to the resultant solution was added dropwise, under ice-cooling 19 mL of a 1.7 M solution of tert-butyllithium in pentane. After 2 hours of reaction at room temperature, the reaction product was incorporated under ice-cooling with 3.25g (30 mmol, 3.8 mL)
 50 of trimethylchlorosilane (TMSCl) that had been subjected to simple distillation, was brought back to room temperature and was allowed to stand overnight. The yellow solution thus obtained was incorporated with 20 mL of water for quenching and THF was removed under reduced pressure. Then, the solution was extracted and separated with 300 mL of hexane, the organic phase thus obtained was dried with magnesium sulfate anhydride as the drying agent, the used drying agent was filtered away, and the volatile components were distilled away under reduced pressure. As the result, there was
 55 produced 1,2,3-trimethylindenyltrimethylsilane in the form of yellow oil in a yield of 4.27g (18.5 mmol) and in a yield rate of 72%.

The product was analyzed by ¹H-NMR by the use of trimethylsilane as the standard and heavy chloroform (CDCl₃) as the solvent with the results as follow : ¹H-NMR; 7.25 to 7.04ppm (4H, m), 2.03ppm (3H, s), 1.93ppm (3H, s), 1.38ppm (3H, s), -0.20ppm (9H, s).


(4) Synthesis of 1,2,3-trimethylindenyltitanium trichloride ---

Titanium tetrachloride in an amount of 4.7g (25 mmol, 2.7 mL) was dissolved in 80 mL of dehydrated toluene, and to the resultant solution was added dropwise, at room temperature, a solution of 4.27g of 1,2,3-trimethylindenyltrimethylsilane in 40 mL of toluene over a period of 3 hours. After one hour of heating refluxing of the mixed solution thus obtained, there was produced a toluene-soluble portion at 80°C, which then was extracted twice with 100 mL each of toluene. By filtering off the toluene-insoluble portion with a filter, there was obtained a green toluene solution, and the volatile components of which were distilled away at 40°C under reduced pressure to afford dark green solid. Thereafter, the solid was incorporated with 20 mL of toluene and then with 200 mL of hexane, and the insoluble portion was collected by filtration as the objective product. Further, a slight amount of decomposed product was removed with boiling hexane. The final product was obtained in a yield of 4.7g (14.5 mmol) and in a yield rate of 58%, and was analyzed by NMR with the results as follows : ¹H-NMR (Tetramethylsilane as the standard and CDCl₃ as the solvent); 7.49 to 7.75 ppm (4H, dq), 2.72ppm (6H, s), 2.53ppm (3H, s), ¹H-NMR (tetramethylsilane as the standard and heavy benzene as the solvent); 7.27 to 6.89ppm (4H, dq), 2.23ppm (6H, s), 1.96ppm (3H, s).

The schematic synthesis process for compound E is illustrated as follows.



In addition, the foregoing (3) 1,2,3-trimethylindenyltrimethylsilane can be synthesized through the process illustrated by the following schematic synthesis process.



Synthesis Example 6

Synthesis of 1,2,3-trimethylindenyltrimethyltitanium (Compound F) ---

1,2,3-trimethylindenyltitanium trichloride in an amount of 0.81g (2.5 mmol) which had been synthesized in Synthesis Example 5 was dissolved in 50 mL of dehydrated THF in an atmosphere of nitrogen. The resultant solution was incorporated under ice-cooling, with 9.0 mL of 1.0 M solution of methylmagnesium bromide in THF, and after the elapse of 15 minutes was gradually brought back to room temperature, with the result that the solution turned to yellowish brown gradually. After the elapse of 30 minutes, the volatile components in the solution were distilled away under reduced pressure to leave only the bone-dried matter, which was extracted with a total quantity of 250 mL of dried hexane. The hexane-insoluble portion was filtered off, and the volatile components in the filtrate solution were distilled away to afford a reddish yellow oil in a yield of 0.59g (2.3 mmol) and in a yield rate of 90%. The oil was allowed to stand overnight in a refrigerator with the result that the oil turned to a yellow solid.

Example 1

In a 30 mL glass ampule which had been dried and purged with nitrogen were placed 10 mL of styrene, 62.5 μ L of 2 mol/L solution of triisobutylaluminum in toluene and 125 μ L of 1 mol/L solution of aluminoxane in toluene, followed by sealing the ampule with a teflon cap, then the ampule was immersed in an oil bath at 70°C and allowed to stand for 15 minutes. Then, to the resultant mixture was added 125 μ L of 10 mmol/L of the Compound A which had been synthesized in Synthesis Example 1 in toluene to proceed with polymerization at 70°C for 4 hours. After the completion of the reaction, the content in the ampule was washed with methanol and dried to recover 0.75g of polymer. The polymer was subjected to Soxhlet extraction for 5 hours by the use of boiling methyl ethyl ketone to produce 0.38g of syndiotactic polystyrene from the insoluble portion. The objective syndiotactic polystyrene having an intrinsic viscosity $[\eta]$ of 0.53 dL/g as measured in trichlorobenzene at 135°C was obtained in a catalytic activity of 13000 g/g \cdot Ti.

Example 2

The procedure in Example 1 was repeated to carry out the polymerization except that there was employed the compound C which had been synthesized in Synthesis Example 3 in place of the compound A. The resultant polymer in an amount of 2.30g was subjected to Soxhlet extraction for 5 hours by the use of methyl ethyl ketone to produce 1.33g of syndiotactic polystyrene from the insoluble portion. The objective syndiotactic polystyrene having an intrinsic viscosity $[\eta]$ of 0.37 dL/g as measured in trichlorobenzene at 135°C was obtained in a catalytic activity of 39,000 g/g · Ti.

Example 3

There was prepared in advance, a catalyst solution by mixing 10 mL of 0.05 mol/L solution of triisobutylaluminum in toluene, 5 mL of 10 mmol/L solution of the compound B which had been synthesized in the Synthesis Example 2 in toluene, 5 mL of 10 mmol/L slurry solution of N,N-dimethylaniliumtetrakis(pentafluorophenyl)borate in toluene and 5 mL of toluene in an atmosphere of nitrogen. Subsequently in a 30 mL glass ampule which had been dried and purged with nitrogen were placed 10 mL of styrene and 5 μ L of triisobutylaluminum, followed by sealing the ampule with a teflon cap. Then the content in the ampule was heated to 60°C and incorporated with 1.25 mL of the above-prepared catalyst solution to proceed with polymerization at 60°C for 4 hours. After the completion of the reaction, the content in the ampule was washed with methanol and dried to recover 0.60g of polymer. The polymer was subjected to Soxhlet extraction for 5 hours by the use of boiling methyl ethyl ketone to produce 0.37g of syndiotactic polystyrene from the insoluble portion. The objective syndiotactic polystyrene having an intrinsic viscosity of 0.62 dL/g as measured in trichlorobenzene at 135°C was obtained in a catalytic activity of 5,000 g/g · Ti.

Example 4

The procedure in Example 3 was repeated to carry out the polymerization except that there was employed the compound D which had been synthesized in Synthesis Example 4 in place of the compound B. The resultant polymer in an amount of 4.75g was subjected to Soxhlet extraction for 5 hours by the use of boiling methyl ethyl ketone to produce 3.94g of syndiotactic polystyrene from the insoluble portion. The objective syndiotactic polystyrene having an intrinsic viscosity $[\eta]$ of 0.45 dL/g as measured in trichlorobenzene at 135°C was obtained in a catalytic activity of 40,000 g/g · Ti.

Example 5

The procedure in Example 3 was repeated to carry out the polymerization except that the polymerization temperature was set to 80°C. The resultant polymer in an amount of 0.95g was subjected to Soxhlet extraction for 5 hours by the use of boiling methyl ethyl ketone to produce 0.43g of syndiotactic polystyrene from the insoluble portion. The objective syndiotactic polystyrene having an intrinsic viscosity $[\eta]$ of 0.48 dL/g as measured in trichlorobenzene at 135°C was obtained in a catalytic activity of 8,000 g/g · Ti.

Example 6

The procedure in Example 4 was repeated to carry out the polymerization except that the polymerization temperature was set to 70°C and 375 μ L of the mixed catalyst solution was employed. The resultant polymer in an amount of 1.16g was subjected to Soxhlet extraction for 5 hours by the use of boiling methyl ethyl ketone to produce 0.78g of syndiotactic polystyrene from the insoluble portion. The objective syndiotactic polystyrene having an intrinsic viscosity $[\eta]$ of 0.40 dL/g as measured in trichlorobenzene at 135°C was obtained in a catalytic activity of 32,500 g/g · Ti.

Example 7

There was prepared in advance a catalyst solution by mixing 10 mL of 0.1 mol/L solution of triisobutylaluminum in toluene, 5 mL of 10 mmol/L solution of the compound F which had been synthesized in the Synthesis Example 6 in toluene, 5 mL of 10 mmol/L slurry solution of N,N-dimethylaniliumtetrakis(pentafluorophenyl)borate in toluene and 5 mL of toluene in an atmosphere of nitrogen. Subsequently in a 30 mL glass ampule which had been dried and purged with nitrogen was placed 10 mL of styrene, followed by sealing the ampule with a teflon cap. The content in the ampule was heated to 70°C and incorporated with 250 μ L of the above-prepared mixed catalyst solution to proceed with polymerization at 70°C for 4 hours. After the completion of the reaction, the content in the ampule was washed with methanol and dried to recover 3.37g of polymer. The polymer was subjected to Soxhlet extraction for 5 hours by the use of boiling methyl ethyl ketone to produce 3.30g of syndiotactic polystyrene from the insoluble portion. The objective syndiotactic polystyrene had a weight-average molecular weight of 1,100,000 and a molecular-weight distribution of 2.1 and was obtained in a catalytic activity of 139,000 g/g · Ti.

INDUSTRIAL APPLICABILITY

The catalyst for producing a styrenic polymer according to the present invention, which comprises a transition metal compound having as a π -ligand, an indenyl group bearing at least one substituent group on the side of its five-membered ring, is imparted with a high activity. By the use of the foregoing catalyst, it is made possible to efficiently produce a styrenic polymer having a high degree of syndiotactic configuration in its aromatic vinyl chain.

Claims

1. A catalyst for producing a styrenic polymer which comprises a transition metal compound having as a π -ligand, an indenyl group bearing at least one substituent group on the side of its five-membered ring.
2. A catalyst for producing a styrenic polymer which comprises an (A) transition metal compound having as a π -ligand, an indenyl group bearing at least one substituent group on the side of its five-membered ring and (B) at least one compound selected from the group consisting of an ① aluminoxane and an ② ionic compound comprising a noncoordinate anion and a cation.
3. A catalyst for producing a styrenic polymer which comprises an (A) transition metal compound having as a π -ligand, an indenyl group bearing at least one substituent group on the side of its five-membered ring, (B) at least one compound selected from the group consisting of ① an aluminoxane and ② an ionic compound comprising a noncoordinate anion and a cation, and (C) a Lewis acid.
4. The catalyst for producing a styrenic polymer according to Claim 1, 2 or 3 wherein the transition metal in said transition metal compound is at least one metal selected from the group consisting of titanium, zirconium, hafnium, lanthanoids, niobium and tantalum.
5. The catalyst for producing a styrenic polymer according to Claim 1, 2 or 3 wherein the substituent group of the indenyl group bearing at least one substituent group on the side of its five-membered ring is an alkyl group having 1 to 20 carbon atoms.
6. The catalyst for producing a styrenic polymer according to Claim 2 or 3 wherein said aluminoxane is a chain aluminoxane or a cyclic aluminoxane.
7. A process for producing a styrenic polymer which comprises polymerizing an (a) styrenic monomer in the presence of the catalyst as set forth in any one of Claims 1 to 6.
8. A process for producing a styrenic polymer which comprises polymerizing an (a) styrenic monomer along with (b) at least one compound selected from olefins, diolefins and alkynes in the presence of the catalyst as set forth in any one of Claims 1 to 6.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP94/01078

A. CLASSIFICATION OF SUBJECT MATTER		
Int. Cl ⁶ C08F4/80, C08F12/08		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
Int. Cl ⁵ C08F4/80, C08F12/08		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP, A, 4-366109 (Idemitsu Kosan Co., Ltd.), December 18, 1992 (18. 12. 92), Claim, (Family: none)	1-6, 7-8
X	JP, A, 5-105712 (Tosoh Corp.), April 27, 1993 (27. 04. 93), Claim, (Family: none)	1-6, 7-8
X	JP, A, 4-366108 (Idemitsu Kosan Co., Ltd.), December 18, 1992 (18. 12. 92), Claim, (Family: none)	1-6, 7-8
X	JP, A, 4-91095 (Mitsui Toatsu Chemicals, Inc.), March 24, 1992 (24. 03. 92), Claim, (Family: none)	1-6, 7-8
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reasons (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "A" document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
September 5, 1994 (05. 09. 94)		September 27, 1994 (27. 09. 94)
Name and mailing address of the ISA/		Authorized officer
Japanese Patent Office		
Facsimile No.		Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)